BSN

Permanent Heat-Seal Film



and borders will not come off. BSN is available in two versions: Use with an iron (type H) or with a heat press (type I).



Main Applications:

Heat-seal film for appliqués, patches and emblems.

For permanent bonding of edges,

borders and seams.

Processing Recommendations:

Coating the emblem:

- Place the emblem with the reverse side on the foil side of BSN and cut out the shape together with the silicone paper adding about 3 mm of extra length.
- Type I: Press with the heat press at 170° C

for approx. 5 seconds. press with an iron 둂

Type H: for approx. 5 sec.

Remove the silicone paper from the coated emblem. Then turn excess backwards. Advantage: Better edge bonding.

Appliqués on garments:

- Iron the base material before use. Fabric finishes evaporate and a permanent fixation is achieved!
- Place the coated emblem on the desired spot and press it on permanently:

Press on with the heat press Type I:

(medium pressure) at 170° C for approx. 15 seconds.

iron thoroughly with an iron Type H:

for approx. 20-25 seconds. Repeat the ironing process on the

back of fabric.



Your own necessary for best bonding Full adhesiveness will be achieved after 48 hours!

Technical Information:

- Foils for ironing on
- Material:

Base: 100% Polyamide Cover: Silicone Paper

Make-up - Types I + H:

Rolls 75 cm x 100 m 37,5 cm x 100 m 37,5 cm x 25 m



Available in 2 different versions:

Type I · suitable for washing up to 60° C

· chemical cleaning possible

· can only be applied with heat press

· Thickness: - Base: 80 g/m²

- Cover: 72 g/m²

Type H · suitable for washing up to 40° C

· chemical cleaning possible

· fixation also possible with an iron

- Base: 60 g/m² · Thickness:

- Cover: 72 g/m²

Minimum Order: 1 roll

Professional materials for high-quality embroidery results - tried and tested in the clothing, promotion and home textile industries. For more information visit our website www.qunold.de!



